

ID label	10β-a	10β-b	10β-c	10β-d	10β-e	10β-f	10β-g	10β-h	10β-i	10β-j	10β-k	10β-l	10β-m	10β-n	10β-o	10β-p	
water factor	×1.0			×1.0			×1.0			×1.2							
DMF(%)	90			100			95			90							
n*	1.0500			1.0500			1.0505			1.0525							

ref. index @405nm		1.0504	1.0505	1.0507	1.0507	1.0526	1.0527	1.0522	1.0525	1.0512	1.0514	1.0514	1.0513	1.0494	1.0499	1.0484	1.0493
transL @400nm	[mm]	39.9	40.6	38.6	39.2	36.4	34.4	37.1	36.3	40.5	42.0	40.9	40.0	25.5	18.0	22.8	20.8

size	length	[mm]	57.8	57.8	57.8	57.8	57.3	57.8	57.5	57.8	57.8	57.8	57.8	57.8	58.3	58.3	58.3	58.3
	width	[mm]	91.8	91.8	91.8	91.8	91.0	91.5	91.0	91.5	91.5	91.5	91.5	91.5	92.3	92.3	92.3	92.3
	thickness	[mm]	9.5	10.3	9.8	10.0	9.8	10.0	9.8	10.3	9.5	10.5	9.8	10.0	10.5	9.8	9.5	10.5
	volume	[cm ³]	31.7	34.2	32.5	33.4	32.0	33.4	32.2	34.2	31.7	35.0	32.5	33.4	35.6	33.1	32.2	35.6

density	[g/cm ³]	0.286	0.285	0.285	0.288	0.289	0.295	0.284	0.289	0.289	0.284	0.289	0.290	0.280	0.286	0.282	0.287
---------	----------------------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------	-------

rez.	ref. index @405nm		0.0006	0.0005	0.0006	0.0005	0.0006	0.0006	0.0005	0.0006	0.0006	0.0006	0.0006	0.0006	0.0021	0.0021	0.0018	0.0021
	transL	[mm]	1.2	1.2	1.2	1.2	1.1	1.0	1.1	1.0	1.3	1.2	1.2	1.2	0.7	0.5	0.6	0.5
	volume	[cm ³]	0.9	0.9	0.9	0.9	0.8	0.9	0.8	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	density	[g/cm ³]	0.008	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.008	0.007	0.007	0.007	0.007	0.007	0.007	0.007
	spot radius @405nm ±1mm	[mm]	2	2	2	2	2	2	2	2	2	2	2	2	8	8	7	8

gel-screen interval	[mm]	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823
spot shift (right) @405nm	[mm]	190.5	190.5	191.5	190.5	199	199	195.5	197	194.5	193.5	194	193	186	188	180	188
		189	190	190	190.5	197.5	198.5	196.5	197.5	193	193.5	192.5	192	185	187	182	186
		188.5	188.5	190.5	190	197.5	198	197	198.5	191	193	192.5	193	185	188	181	182
		189	189.5	190.5	191.5	197.5	198	197	197.5	192	192.5	193.5	194.5	186	187	183	185
transT @400nm	[%T]	78.8	77.7	77.7	77.5	76.5	74.8	76.9	75.4	79.1	77.9	78.8	77.9	66.3	58.1	65.9	60.3
thickness ±0.25mm	[mm]	9.50	10.25	9.75	10.00	9.75	10.00	9.75	10.25	9.50	10.50	9.75	10.00	10.50	9.75	9.50	10.50
		9.50	10.25	9.75	10.00	9.75	10.00	9.75	10.25	9.50	10.50	9.75	10.00	10.50	9.75	9.50	10.50
		9.50	10.25	9.75	10.00	9.75	10.00	9.75	10.25	9.50	10.50	9.75	10.00	10.50	9.75	9.50	10.50
		9.50	10.25	9.75	10.00	9.75	10.00	9.75	10.25	9.50	10.50	9.75	10.00	10.50	9.75	9.50	10.50

demension (detail) ±0.25mm	[mm]	91.75	91.75	91.75	91.75	91.00	91.50	91.00	91.50	91.50	91.50	91.50	91.50	91.50	92.25	92.25	92.25	92.25
		57.75	57.75	57.75	57.75	57.25	57.75	57.50	57.75	57.75	57.75	57.75	57.75	57.75	58.25	58.25	58.25	58.25
		91.75	91.75	91.75	91.75	91.00	91.50	91.00	91.50	91.50	91.50	91.50	91.50	91.50	92.25	92.25	92.25	92.25
		57.75	57.75	57.75	57.75	57.25	57.75	57.50	57.75	57.75	57.75	57.75	57.75	57.75	58.25	58.25	58.25	58.25
long. shrinkage ratio (□95.0mm)		0.966	0.966	0.966	0.966	0.958	0.963	0.958	0.963	0.963	0.963	0.963	0.963	0.971	0.971	0.971	0.971	

weight	[g]	9.05	9.74	9.26	9.59	9.23	9.85	9.14	9.88	9.17	9.93	9.41	9.67	9.99	9.45	9.09	10.22
--------	-----	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	-------

crack		なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし
-------	--	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----	----

comment		欠損	欠損	欠損	欠損	欠損	欠損						欠損	スポット不明瞭、反り大	スポット不明瞭、反り大	スポット不明瞭、反り大	スポット不明瞭、反り大
---------	--	----	----	----	----	----	----	--	--	--	--	--	----	-------------	-------------	-------------	-------------