

ID label		8a-a	8a-b	8a-c	8a-d	8a-e	8a-f	8a-g	8a-h	8a-i	8a-j	8a-k	8a-l	8a-m	8a-n	8a-o	8a-p	
water factor		×1.0				×1.0				×1.0				×1.0				
DMF(%)		85				90				95				100				
ref. index @405nm		1.0487	1.0486	1.0486	1.0487	1.0491	1.0491	1.0495	1.0494	1.0497	1.0497	1.0494	1.0496	1.0501	1.0501	1.0502	1.0502	
transL @400nm	[mm]	37.6	39.4	37.6	38.4	34.6	38.3	38.0	38.3	38.5	38.8	40.1	40.5	39.0	40.1	36.5	37.3	
size	length	[mm]	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.0	58.0	58.0	58.0
	width	[mm]	92.3	92.3	92.5	92.5	92.3	92.3	92.3	92.3	92.3	92.3	92.3	92.3	92.0	92.0	92.0	92.0
	thickness	[mm]	9.0	11.1	9.3	10.8	10.0	10.3	9.4	10.5	10.3	9.8	9.5	10.3	9.3	11.0	9.5	10.3
	volume	[cm <sup>3</sup> ]	30.5	37.5	31.4	36.5	33.9	34.8	32.0	35.6	35.0	33.1	32.2	35.0	31.1	37.0	32.0	34.5
density	[g/cm <sup>3</sup> ]	0.274	0.275	0.277	0.277	0.271	0.277	0.276	0.282	0.278	0.279	0.280	0.282	0.278	0.279	0.287	0.285	
rez.	ref. index @405nm		0.0006	0.0006	0.0006	0.0005	0.0006	0.0004	0.0005	0.0004	0.0005	0.0005	0.0006	0.0005	0.0007	0.0006	0.0006	0.0005
	transL	[mm]	1.2	1.1	1.2	1.1	1.0	1.1	1.2	1.1	1.1	1.2	1.2	1.2	1.1	1.1	1.1	1.1
	volume	[cm <sup>3</sup> ]	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	density	[g/cm <sup>3</sup> ]	0.008	0.006	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.008	0.006	0.008	0.007
	spot radius @405nm +1mm	[mm]	2	2	2	2	2	1	2	1	2	2	2	2	3	2	2	2
gel-screen interval	[mm]	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	
spot shift (right) @405nm	[mm]	182	182	182	182.5	183.5	184.5	186.5	185.5	186.5	187	186	185.5	187.5	187.5	189.5	188.5	
		183.5	183	182	183.5	185.5	184	185.5	186	187.5	187.5	186	186.5	188	188.5	189	189	
		183	182	182	181.5	185	184.5	186	185	186	186	185.5	186	188.5	189	188	188	
		182.5	182.5	183.5	183	184	185	186	186	186.5	185	185	186.5	189	188.5	187.5	188.5	
transT @400nm	[%T]	78.7	75.5	78.2	75.6	74.9	76.5	78.0	76.0	76.5	77.8	78.9	77.5	78.9	76.0	77.1	76.0	
thickness ±0.25mm	[mm]	9.00	11.00	9.25	10.75	10.00	10.25	9.50	10.50	10.25	9.75	9.50	10.50	9.25	11.00	9.50	10.25	
		9.00	11.00	9.25	10.75	10.00	10.25	9.50	10.50	10.25	9.75	9.50	10.25	9.25	11.00	9.50	10.25	
		9.00	11.25	9.25	10.75	10.00	10.25	9.50	10.50	10.50	9.75	9.50	10.25	9.25	11.00	9.50	10.25	
		9.00	11.00	9.25	10.75	10.00	10.25	9.25	10.50	10.25	9.75	9.50	10.25	9.25	11.00	9.50	10.25	
demension (detail) ±0.25mm	[mm]	92.25	92.25	92.50	92.50	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.00	92.00	92.00	92.00
		58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.00	58.00	58.00	58.00
		92.25	92.25	92.50	92.50	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.25	92.00	92.00	92.00	92.00
		58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.00	58.00	58.00	58.00
long. shrinkage ratio (□95.0mm)		0.971	0.971	0.974	0.974	0.971	0.971	0.971	0.971	0.971	0.971	0.971	0.971	0.968	0.968	0.968	0.968	
weight	[g]	8.37	10.33	8.68	10.10	9.20	9.65	8.84	10.04	9.73	9.22	9.02	9.86	8.65	10.33	9.16	9.83	
crack		なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	
comment						欠損					欠損		欠損	欠損			底にゴミ 1	