

ID label		8β-a	8β-b	8β-c	8β-d	8β-e	8β-f	8β-g	8β-h	8β-i	8β-j	8β-k	8β-l	8β-m	8β-n	8β-o	8β-p	
water factor		×1.1				×1.1				×1.1				×1.1				
DMF(%)		85				90				95				100				
ref. index @405nm		1.0488	1.0484	1.0486	1.0485	1.0486	1.0485	1.0489	1.0488	1.0490	1.0490	1.0490	1.0491	1.0492	1.0492	1.0499	1.0497	
transL @400nm	[mm]	37.8	38.3	35.7	36.8	32.0	30.4	35.4	35.1	30.1	30.9	36.5	37.0	38.1	38.5	25.9	26.3	
size	length	[mm]	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.0	58.0	58.0	58.0
	width	[mm]	92.3	92.3	92.5	92.5	92.3	92.5	92.5	92.3	92.3	92.3	92.3	92.3	92.0	92.0	92.0	92.0
	thickness	[mm]	9.3	10.8	9.8	10.3	10.3	9.8	9.3	10.8	9.5	10.8	9.5	10.5	10.3	10.0	10.0	10.3
	volume	[cm <sup>3</sup> ]	31.4	36.5	33.1	34.8	34.8	33.1	31.4	36.5	32.2	36.5	32.2	35.6	34.5	33.6	33.6	34.5
density	[g/cm <sup>3</sup> ]	0.273	0.277	0.278	0.273	0.276	0.276	0.274	0.278	0.275	0.273	0.279	0.277	0.278	0.276	0.277	0.277	
rez.	ref. index @405nm		0.0006	0.0006	0.0006	0.0006	0.0006	0.0005	0.0006	0.0005	0.0008	0.0005	0.0006	0.0005	0.0005	0.0005	0.0006	0.0006
	transL	[mm]	1.2	1.0	1.1	1.0	0.9	0.9	1.1	0.9	0.9	0.8	1.1	1.0	1.1	1.1	0.7	0.7
	volume	[cm <sup>3</sup> ]	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9	0.9
	density	[g/cm <sup>3</sup> ]	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.007	0.006	0.007	0.007	0.007	0.007	0.007	0.007
	spot radius @405nm +1mm	[mm]	2	2	2	2	2	2	2	2	3	2	2	2	2	2	2	2
gel-screen interval	[mm]	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	1823	
spot shift (right) @405nm	[mm]	184	181	182.5	181.5	182	181	183	183	184	183.5	185	184	183.5	185	188	187.5	
		183.5	182.5	182	181.5	182.5	183	184	183	184.5	184	183.5	184.5	185	186	187.5	187	
		181.5	181.5	182	183.5	181.5	181.5	183.5	183.5	184	184	183	184.5	185.5	184	187	185	
		183	182	183	181.5	183	182.5	184	183.5	183.5	184	184.5	184	184.5	184.5	187	187.5	
transT @400nm	[%T]	78.3	75.5	76.1	75.7	72.6	72.6	77.0	73.6	72.9	70.6	77.1	75.3	76.4	77.1	68.0	67.7	
thickness ±0.25mm	[mm]	9.25	10.75	9.75	10.25	10.25	9.75	9.25	10.75	9.50	10.75	9.50	10.50	10.25	10.00	10.00	10.25	
		9.25	10.75	9.75	10.25	10.25	9.75	9.25	10.75	9.50	10.75	9.50	10.50	10.25	10.00	10.00	10.25	
		9.25	10.75	9.75	10.25	10.25	9.75	9.25	10.75	9.50	10.75	9.50	10.50	10.25	10.00	10.00	10.25	
		9.25	10.75	9.75	10.25	10.25	9.75	9.25	10.75	9.50	10.75	9.50	10.50	10.25	10.00	10.00	10.25	
demension (detail) ±0.25mm	[mm]	92.25	92.25	92.50	92.50	92.25	92.50	92.50	92.25	92.25	92.25	92.25	92.25	92.25	92.00	92.00	92.00	92.00
		58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.00	58.00	58.00	58.00
		92.25	92.25	92.50	92.50	92.25	92.50	92.50	92.25	92.25	92.25	92.25	92.25	92.25	92.00	92.00	92.00	92.00
		58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.25	58.00	58.00	58.00	58.00
long. shrinkage ratio (□95.0mm)		0.971	0.971	0.974	0.974	0.971	0.974	0.974	0.971	0.971	0.971	0.971	0.971	0.968	0.968	0.968	0.968	
weight	[g]	8.56	10.11	9.19	9.48	9.60	9.13	8.60	10.15	8.88	9.95	8.99	9.88	9.60	9.28	9.32	9.56	
crack		なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	なし	
comment			欠損	欠損		欠損	欠損		欠損、レンズ状 ヒビ1		欠損	欠損		欠損	欠損	欠損、レンズ状 ヒビ1		